

Ultraleather™



291-3491 Wet Sand



291-3851 Chamois



291-3778 Pecan



291-3779 Taupe



291-8243 Apricot



291-1256 Papyrus




291-3523 Cave



291-6588 Salmon




291-1334 Toro



291-5243 Lemon



291-4460 Parrot



291-4454 Sonora



291-3777 Walnut



291-2553 Cyan



291-2555 Nile



291-2556 Admiral



291-9380 Dusk



291-5684 Arctic



291-5666 Dove Grey



291-5763 Charcoal



291-5607 Raven Wing

Ultraleather™

Features/Benefits

- Incredibly soft, supple and luxurious.
- Inherently stain resistant, low maintenance to stay looking its best.
- Technology enhanced bond, seam and tear strength.
- Thermal comfort - remains cool to the touch, even in sunlight.

Earth Friendly

- **Greenguard® Certified**
- No PVC (Polyvinyl Chloride)
- No POPs (Persistent Organic Pollutants)
- No PBDEs (Polybrominated Diphenyl Ethers)
- No HFRs (Halogenated Flame Retardants)
- Meets the most stringent VOC standards
- No Plasticizers, Heavy Metals, Stabilizers, Phthalates or Bisphenol A (BPA)
- No toxic by-products
- Over 99% of solvents recaptured and recycled

Maintenance & Care Instructions

Keep Ultrafabrics, LLC brand surfaces looking great by routine and proper maintenance. Follow these guidelines to extend the life of the fabric:

- Clean regularly with soap and water
- Wipe up spills as soon as they occur
- Remove stains with alcohol-based cleaners like Fantastik® and Formula 409®
- Clean/disinfect using a 5:1 water/bleach solution
- Thoroughly rinse all solution residue with clean water
- Air dry



Boyd Industries
12900 44th St N
Clearwater, FL 33762
Toll Free 800-255-2693

www.boydindustries.com

SPECIFICATIONS

COMPOSITION:	100% POLYURETHANE SURFACE 100% REINFORCED RAYON BACKING
WEIGHT:	APPROX. 9.7 OZ. PER SQUARE YARD (APPROX. 330 GRAMS PER SQUARE METRE)
	APPROX. 14.6 OZ. PER LINEAR YARD (APPROX. 450 GRAMS PER LINEAR METRE)
THICKNESS:	APPROX. 0.95 MILLIMETRES
WIDTH:	54 INCHES / 137 CENTIMETRES
PUT-UP:	APPROX. 33 YDS / 30 METRES R.O.T.

PERFORMANCE PROPERTIES:

PERFORMANCE PROPERTIES:	STANDARD:
ABRASION:	ASTM D 4157 / 400,000 DOUBLE RUBS (WYZENBEEK)* BS 2543 / 180,000 RUBS (MARTINDALE)* <small>*MEETS OR EXCEEDS</small>

DIMENSIONAL CHANGE:	ASTM D 3597
---------------------	-------------

HYDROLYSIS:	ASTM D3690-02 SECT. 6.11 (HYDROLYTIC STABILITY) ISO 1419 METHOD C (ACCELERATED AGEING)
-------------	---

SEAM STRENGTH:	ASTM D 751
----------------	------------

STRETCH & SET:	SAE J855
----------------	----------

TEAR STRENGTH:	ASTM D 1117
----------------	-------------

TENSILE STRENGTH:	ASTM D 1117
-------------------	-------------

COLORFASTNESS:

CROCKING:	AATCC 8, CLASS 5 WET & DRY
-----------	----------------------------

LIGHT:	AATCC 16E, AATCC 16A, CLASS 4-5 ISO 105 - B02 : 1999 GRADE 7/8
--------	---

GAS:	AATCC 23, CLASS 5
------	-------------------

OZONE:	AATCC 109, CLASS 5
--------	--------------------

F/R RATING:

ASTM E 84 (ADHERED)	CLASS A
CA 117 E	CLASS 1
FMVSS 302 & 95/28 ANNEX IV	PASS
NFPA 260	CLASS 1
UFAC	CLASS 1

PLEASE NOTE:

THESE FABRICS, WHEN TREATED AND/OR USED WITH OTHER COMPATIBLE FURNITURE COMPONENTS, HAVE BEEN SHOWN TO PERFORM WELL UNDER THE FIRE TEST CONDITIONS OF:

- FAR SPECIFICATIONS
- ASTM E 84 (UNADHERED)
- CALIFORNIA TECHNICAL BULLETIN 133
- NFPA 701
- IMO A.652 (16)
- BS 5852 PT 0, 1 & 5 (CRIB 5)
- BS 5867 PART 2 TYPE B
- BS 7175



Scan code to place sample request